



Product Data

Optigear OG 4 EP

Open Gear Lubricant

Description

Castrol Optigear™ OG 4 EP is developed for use in rolls and open gears, beds and bearings subject the high loads, applied by bath or spray. Optigear OG 4 EP is based on high viscosity base oil in combination with EP (Extreme Pressure) additive technology to provide optimum protection of gears / bearings.

Application

Optigear OG 4 EP is designed for open gears, rolling or slide bearings and guides. Supports high loads and with high adherence properties, maintaining a constant film on the metallic surfaces, even in vertical positions.

The product is designed to be used specifically in Type 2 open gears in Cement mills and kilns, Power Generation coal mills, Mining and Ore processing mills, SAG mills and Pebble mills. Optigear OG 4 EP can also used for heavy loaded antifriction and plain bearings.

Advantages

- Excellent lubricant properties (it reduces the working temperatures, when compared to asphaltic lubricants).
- High adhesiveness remaining in place even on vertical equipment.
- High capacity of supporting loads.
- Excellent corrosion protection and oxidation resistance.
- Excellent behavior viscosity / temperature (high viscosity index).
- Can increase of the useful life of equipment.

Typical Characteristics

Name	Method	Units	OG 4 EP
Colour	ASTM D1500	-	Amber
Density @ 20°C / 68°F	ASTM D4052 / ISO 12185	kg/m ³	924
Kinematic Viscosity @ 40°C / 104°F	ASTM D445 / ISO 3104	mm ² /s	13000
Kinematic Viscosity @ 100°C / 212°F	ASTM D445 / ISO 3104	mm ² /s	550
Viscosity Index	ASTM D2270 / ISO 2909	-	201
Flash Point - open cup method	ASTM D92 / ISO 2592	°C/°F	220
Steel Corrosion	ASTM D 665 - A	-	Pass
FZG Gear Scuffing test - A/8.3/90	ISO 14635-1	-	>12
Four Ball Weld Load test - Weld Point	ASTM D2783	kgf	>800
Falex V-Block, weld load lb 3000+	ASTM D 3233	lb	>3000
Falex V-Block, wear (750 lb / 30 min.)	ASTM D 2670 Modified	Teeth	0 (zero)

Subject to usual manufacturing tolerances.

Optigear OG 4 EP
14 Feb 2024

Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

Castrol Industrial, Technology Centre , Whitchurch Hill , Pangbourne , Reading , RG8 7QR , United Kingdom

<http://msdspds.castrol.com>